


DIN-32895-Ø8x24x11,5mm Chain (KG824A)



Properties & Notes		Tolerances for Total Meters in Production	
Material	Alloy Steel	1,008mt - 42link	Min : 1008mm
Standards for manufacturing and testing	DIN -32895		Max : 1011mm
Breaking Force (BF)	Min 71 kN	4,992mt - 208link	Min : 4992mm
Manufacturing Proof Force (MPF)	45 kN		Max : 5007mm
Working Load Limit (WLL)	Max 17 kN	10,008mt - 417-418link	Min : 10008mm
			Max : 10038mm
Ultimate Elongation (A)	% 10 min	25,008mt - 1042-1045link	Min : 25008mm
			Max : 25083mm
Bend Deflection (f)	7 mm Min	49,992mt - 2083-2089link	Min : 49992mm
			Max : 50142mm
		100,008mt - 4167-4179link	Min : 100008mm
			Max : 100308mm

NOTE : Unless otherwise stated, the tolerances in the table apply. However, for double chain strips, the maximum difference between them should not exceed 0.1%.